

# TECHNICAL DATASHEET

## Rostskyddsmassa/Rustbeskyttelsesmasse/Ruostesuoja- massa

### 36-2411

#### General

36-2411 is a thixotropic, chemically stabilized product consisting of bitumen, waxes, rust inhibitors and solvents. The product is used on the underside of the vehicle and offers preventive rust protection and reliable abrasion protection.

#### Range of application

36-2411 is especially composed for car underbody and can be applied by conventional high-pressure pumps in different thicknesses. The product gives a good anticorrosive protection, de-icing salt protection and some abrasion protection depending on thickness applied. 36-2411 is also suitable for long time outdoor storing of industrial products, for example untreated steel surfaces, machines etc.

#### Instructions for use

Make sure that the surface is dry and free from oil, dirt and rust. Equipment for airless high pressure spraying 1:26> is recommended for treatment of car under bodies and fenders. The product can also be brushed on. Apply several layers where increased protection is required. The car is ready for usage immediately after application.

#### Technical data

Color:	Black
Consistency:	Thixotropic
Type of film:	Elastic, dry film
Density:	1000 ± 20 kg/m <sup>3</sup>
Dry content:	68 ± 3 %
Solvent:	White spirit
Film thickness:	150 – 350 µm
Application temperature:	15 – 25 °C
Removal with:	White spirit or degreasing compound
Storing time:	12 months
Storing temperature:	5 – 35 °C

For further information we recommend the safety data sheet or instruction on package