

TECHNICAL DATASHEET

36-2412, 36-2425

Rostskyddsmassa/Rustbeskyttelsesmasse/Ruostesuoja- massa

General

36-2412, 36-2425 is a rubberized bitumen compound in paste form. The material acts preventively against rust attacks, giving a reliable abrasion resistance and a high sound deadening effect at the same time. 36-2412, 36-2425 maintains its elasticity for a long time irrespective of temperature conditions.

Range of application

36-2412, 36-2425 is mainly intended for use on the underbody of the car and inside the wheel housing where powerful protection is needed. The product can also provide a good protection against de-icing salt and it is water and moisture-repellent.

Instructions for use

The surface shall be dry and clean. Provides good adhesion to previously rust protected surfaces. Apply with brush or knife in a layer of 3-6 mm. Can also be supplied in sprayable form. In that case a spray gun with 6 mm nozzle is recommended.

Technical data

Color:	Black
Consistency:	Thick compound
Type of film:	Plastic, elastic
Density at 20 C:	Ca 1050 kg/m ³
Film thickness:	1 – 3 mm dry film
Temp at application:	15 – 35 °C
Solvent:	White spirit
Removal with:	White spirit or degreasing compound
Dilution:	White spirit
Material usage:	1 – 5 kg/m ²
Flash point:	40 °C
Drying time:	Dry to touch after max 48 h
Storage time:	12 months
Storage temperature:	5 – 35 °C